

ProMar 200 Zero VOC Finishes: A COMPARISON

	Flat	Low sheen eg-shel	Low gloss eg-shel	Eg-shel	Semi-gloss	Gloss
Volume Solids	34%	44%	41%	42%	38%	36%
Data Page Gloss 60° (air dry)	N/A	0-5°	<5°	5° +	25-35°	60-70°
Data Page Sheen 85° (air dry)	1.5-3.5°	20-30°	15-20°	15-20°	N/A	N/A
Ease of Application (ICI)	★★★★★	★★★★↓	★★★★★	★★★★★★	★★★★↓	★★★★↓
Overall Hide	★★★★★	★★★★★	★★★★★	★★★★★	★★★★↓	★★★★★
Blocking	★★★★★★	★★★★★★↓	★★★★	★★★★	★★★★	★★
Washability	★★★★	★★★↓	★★★★↓	★★★★↓	★★★★★	★★★★
Burnish	★★★★	★★★★	★★★★	★★★★★	★★★★	★★★★
Scrubability	★★★★★	★★★↓	★★★★★	★★★★★★	★★★★★★	★★★★★★

★★★★★★ Excellent | ★★★★★ Great | ★★★ Average | ★★ Good | ★ Poor